

UNANNOUNCED

AFML TECHNICAL LIBRARY
OFFICIAL FILE COPY

0

MECHANICAL-PROPERTY DATA
2021 ALUMINUM

AD-820293

Plate (-T8E31)

Issued by

Air Force Materials Laboratory
Research and Technology Division
Air Force Systems Command
Wright-Patterson Air Force Base, Ohio

June, 1967

DISSEMINATION S. ELEMENT P. Further dissemination only as directed
by: ~~Wright-Patterson Air Force Base, Ohio 45433-0523~~
or higher DOD authority. 4 FEB 1985

Prepared by

Battelle Memorial Institute
Columbus Laboratories
Columbus, Ohio 43201

AF 33(615)-2494



DTIC FILE COPY

85 01 25 030

This data sheet was prepared by Battelle Memorial Institute under Contract AF 33 (615)-2494. The contract was initiated under Project No. 7381, "Materials Application", Task No. 738106, "Design Information Development". The major objectives of this program are to evaluate newly developed structural materials of potential Air Force weapons-system interest and then to provide data-sheet-type presentations of mechanical data. The program was assigned to the Structural Materials Engineering Division at Battelle under the supervision of Mr. Walter S. Hyler. Project engineer was Mr. Omar Deel. The program was administered under the direction of the Air Force Materials Laboratory, Air Force Systems Command, Wright-Patterson Air Force Base, Ohio, by Mr. Marvin Knight, project engineer.

Notices

When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may be in any way related thereto.

Qualified requesters may obtain copies of this data sheet from the Defense Documentation Center, Washington, D.C.

~~This document is subject to special export controls and each transmittal to foreign governments or foreign nationals may be made only with the prior approval of the Materials Application Division (MAAM), AFML, Wright-Patterson Air Force Base, Ohio.~~

2021 Aluminum

2021 is a newly developed, weldable, high-strength aluminum alloy. It has been developed as a candidate material for cryogenic structure and tankage applications with particular reference to the requirements of liquid-propellant space boosters. Preliminary studies have shown that this alloy is suitable for fabrication in plate thicknesses and compares favorably with other high-strength aluminum alloys in resistance to corrosion and stress-corrosion cracking.

2021 is not yet commercially available.

~~DISTRIBUTION STATEMENT F: Further dissemination only as directed by: AFORP4 GL15 WAFD 34325-3~~
~~or higher DoD authority.~~

4 FEB 1985

Accession For	
IC & CRA&I	<input type="checkbox"/>
PROT TPS	<input type="checkbox"/>
Unclassified	<input checked="" type="checkbox"/>
Justification	
By	
Distribution/	
Referenceability Codes	
Printed and/or	
Plotted Special	

(5 pp) (5 fig.) (1 tpls.) (0 ref.)

~~F5~~



2021 Data(a)

Condition: -T8E31
 Thickness: 0.250 in. Plate

Properties	Temperature, F			
	-320	-105	RT	300
<u>Tension</u>				
F_{tu} (longitudinal), ksi	85.4	74.3	69.7	55.9
F_{tu} (transverse), ksi	88.6	77.1	73.5	56.8
F_{ty} (longitudinal), ksi	71.0	60.5	58.2	51.6
F_{ty} (transverse), ksi	71.2	59.8	59.5	51.5
e_t (longitudinal) percent in 2 in.	13.8	17.2	14.8	13.5
e_t (transverse), percent in 2 in.	11.0	11.5	10.8	12.0
E_t (longitudinal), 10^6 psi	11.6	11.3	10.1	9.0
E_t (transverse), 10^6 psi	11.7	10.8	10.4	9.5
<u>Compression</u>				
F_{cy} (longitudinal), ksi	74.2	63.1	62.3	56.4
F_{cy} (transverse), ksi	77.3	65.4	63.7	57.6
E_c (longitudinal), 10^6 psi	12.3	11.7	11.0	10.0
E_c (transverse), 10^6 psi	12.2	11.6	11.2	10.2
<u>Shear (b)</u>				
F_{su} (transverse), ksi	U ^(c)	U	45.0	U
F_{su} (transverse), ksi	U	U	46.8	U
<u>Impact (V-notch Charpy)</u>	U	U	U	U
<u>Fracture Toughness, K_{Ic}, ksi $\sqrt{\text{in.}}$</u>	U	U	No pop-in ^(d)	U
<u>Axial Fatigue (transverse)^(e)</u>				
Unnotched, $R = 0.1$				
10^3 cycles, ksi	94	U	80	68
10^5 cycles, ksi	80	U	60	48
10^7 cycles, ksi	59	U	39	20

Properties	Temperature, F			
	-320	-105	RT	300
Notched ($K_t = 3.0$), $R = 0.1$				
10^3 cycles, ksi	75	U	57	46
10^5 cycles, ksi	33	U	25	19
10^7 cycles, ksi	20	U	15	11

	Temperature, F		
	RT	300 F	500 F

Creep (transverse)

0.2% elongation, 100 hr, ksi	NA(c)	33	7.7
0.2% elongation, 1000 hr, ksi	NA	27	5.0

Stress Rupture (transverse)

Rupture 100 hr, ksi	NA	36	10.4
Rupture 1000 hr, ksi	NA	29	5.5

Stress Corrosion

80% F_{ty} , 1000 hr max.	Failed(f)	U	U
-----------------------------	-----------	---	---

Coefficient of Thermal Expansion

13.2×10^{-6} in./in./F (68-212 F)(g)

Density 0.101 lb/in.³(g)

(a) Data are average of triplicate tests conducted at Battelle under the subject contract unless otherwise indicated. Fatigue, creep, and stress-rupture values are from data curves generated using the results of a greater number of tests.

(b) Single shear sheet type specimen, full thickness.

(c) U, unavailable; NA, not applicable.

(d) Fatigue-cracked single-edge-notched specimen (1/4" x 3" 12") tested in tension. No pop-in detected.

(e) "R" represents the algebraic ratio of the minimum stress to the maximum stress in one cycle; that is, $R = S_{\min.}/S_{\max.}$. " K_t " represents the Neuber-Peterson theoretical stress-concentration factor.

(f) Three-point bend test. Alternate immersion 3-1/2% NaCl. All specimens failed. First signs of cracking appeared within 24 hours. Elapsed time between first signs of cracking and failure was 4 days.

(g) Values from private communication with ALCOA.




FIGURE 1. EFFECT OF TEMPERATURE ON THE TENSILE PROPERTIES OF 2021-T8E31 ALUMINUM ALLOY PLATE




FIGURE 2. EFFECT OF TEMPERATURE ON THE COMPRESSIVE PROPERTIES OF 2021-T8E31 ALUMINUM ALLOY PLATE




FIGURE 3. AXIAL LOAD FATIGUE RESULTS FOR 2021-T8E31
AT THREE TEMPERATURES




FIGURE 4. AXIAL LOAD FATIGUE RESULTS FOR NOTCHED ($K_t = 3.0$)
2021-T8E31 AT THREE TEMPERATURES




FIGURE 5. STRESS-RUPTURE AND 0.2% PLASTIC DEFORMATION CURVES FOR 2021-T8E31 AT TWO TEMPERATURES

A-56462